

PA 6 , high viscosity, for extrusion grade and film application, natural color.

Property	Test Condition	Unit	Standard	Value	Value
<b>Rheological properties</b>				D.A.M	Moisture Content
Melt volume - flow rate	235 °C;5 kg	cm <sup>3</sup> /(10min)	ISO 1133	-	
Molding shrinkage, parallel	60x60x2mm/MT 80°C	%	ISO 294	1.8	
Molding shrinkage, normal	60x60x2mm/MT 80°C	%	ISO 294	1.9	
<b>Mechanical properties</b>					
Tensile modulus	1 mm/min	Mpa	ISO 527-1,-2	-	-
Tensile Stress at break	50 mm/min	Mpa	ISO 527-1,-2	75	-
Tensile Strain at break	50 mm/min	%	ISO 527-1,-2	250	-
Tensile creep modulus	1 h	Mpa	ISO 899-1	-	-
Tensile creep modulus	1000 h	Mpa	ISO 899-1	-	-
Charpy impact strength	23°C	kJ/m <sup>2</sup>	ISO 179-1eU	NB	-
Charpy impact strength	-30°	kJ/m <sup>2</sup>	ISO 179-1eU	-	-
Charpy notched impact strength	23°C	kJ/m <sup>2</sup>	ISO 179-1eA	6.2	-
Charpy notched impact strength	-30°C	kJ/m <sup>2</sup>	ISO 179-1eA	-	-
Izod impact strength	23°C	kJ/m <sup>2</sup>	ISO 180-1U	NB	-
Izod impact strength	-30°C	kJ/m <sup>2</sup>	ISO 180-1U	-	-
Izod notched impact strength	23°C	kJ/m <sup>2</sup>	ISO 180-1A	6.0	-
Izod notched impact strength	-30°C	kJ/m <sup>2</sup>	ISO 180-1A	-	-
Izod notched impact strength	-40°C	kJ/m <sup>2</sup>	ISO 180-1A	-	-
Flexural modulus	5 mm/min	MPa	ISO 178	2400	-
Flexural strength	5 mm/min	Mpa	ISO 178	110	-
Flexural strain at flexural strength	2 mm/min	%	ISO 178	-	-
Flexural stress at 3.5% strain	2 mm/min	Mpa	ISO 178	-	-
Shore D hardness		N/mm <sup>2</sup>	ISO 7619	80	-
<b>Thermal properties</b>					
Melting temperature	10°C/min	°C	ISO 11357-1,-3	220	
Temperature of deflection under load	1.80 MPa	°C	ISO 75-1,-2	65	
Temperature of deflection under load	0.45 MPa	°C	ISO 75-1,-2	-	
Temperature of deflection under load	8.00 MPa	°C	ISO 75-1,-2	-	
Vicat softening temperature	50 N; 50°C/h	°C	ISO 306	-	
Coefficient of linear thermal expansion, parallel	23 to 55°C	10 <sup>-4</sup>	ISO 11359-1,-2	-	
Coefficient of linear thermal expansion, transverse	23 to 55°C	10 <sup>-4</sup>	ISO 11359-1,-2	-	
Burning behavior UL 94	1.6 mm	Class	UL 94		HB
Burning behavior UL 94	3.2 mm	Class	UL 94		-
Oxygen index	Method A	%	ISO 4589-2	-	
Glow wire test (GWFI)	2.0 mm	°C	IEC 60695-2-12	-	
Burning rate (US-FMVSS)	d = 1,01mm	mm/min	ISO 3795	-	
<b>Electric properties</b>					
Relative permittivity	100 Hz		IEC 60250	-	
Relative permittivity	1 MHz		IEC 60250	-	
Electric strength	1 mm	kV/mm	IEC 60243-1	-	
Comparative tracking index CTI	Solution A	Rating	IEC 60112	-	
Comparative index CTI M	Solution B	Rating	IEC 60112	-	
Electrolytic corrosion		Rating	IEC 60426	-	
<b>Other properties (23°C)</b>					
Water absorption	Water at 23°C/24hr	%	ISO 62	-	
Moisture absorption (Equilibrium value)	23°C; 50 % RH	%	ISO 62	-	
Density		kg/m <sup>3</sup>	ISO 1183	1.12	
Glass fiber / glass bead / filler content		%	ISO 3451-1	<0.1	
Bulk density		kg/m <sup>3</sup>	ISO 60	-	
<b>Processing conditions for test specimens</b>					
Injection molding - Melt temperature		°C	ISO 294	230-275	
Injection molding - Mold temperature		°C	ISO 294	80-120	
Drying temperature		°C	-	80	
Drying time dry air dryer		h	-	2-6	
Residual moisture content		%	Karl Fischer	<0.1	

#### Disclaimer

Disclaimer for sales products

This information and our technical advice - whether verbal, in writing or by way of trials - are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to verify the information currently provided - especially that contained in our safety data and technical information sheets - and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold and our advisory service is given in accordance with the current version of our General Conditions of Sale and Delivery.

#### Test values

Unless specified to the contrary, the values given have been established on standardized test specimens at room temperature. The figures should be regarded as guide values only and not as binding minimum values. Kindly note that, under certain conditions, the properties can be affected to a considerable extent by the design of the mould/die, the processing conditions and the colouring.

#### Processing note

Under the recommended processing conditions small quantities of decomposition product may be given off during processing. To preclude any risk to the health and well-being of the machine operatives, tolerance limits for the work environment must be ensured by the provision of efficient exhaust ventilation and fresh air at the workplace in accordance with the Safety Data Sheet. In order to prevent the partial decomposition of the polymer and the generation of volatile decomposition products, the prescribed processing temperatures should not be substantially exceeded. Since excessively high temperatures are generally the result of operator error or defects in the heating system, special care and controls are essential in these areas.